HTL

Gold & Precious Metals

FOOD SAFE | NON TOXIC | LEAD FREE | READY TO USE

HTL

Gold & Precious Metals for Ceramics and Porcelain

12% Gold Content

Bright Gold

HTL 8	2g
HTL 8	5g
HTL 8	25g

10% Gold Content

Bright Gold

HTL 2	2g
HTL 2	5g
HTL 2	25g

10% Gold Content

Lemon Gold

HTL 3	2g
HTL 3	5g
HTL 3	25g

8% Gold Content

Bright Gold

HTL 1	2g
HTL 1	5g
HTL 1	25g

Bright Platinum

HTL 4	2g
HTL 4	5g
HTL 4	25g

*M.P. *Gold Content*

Bronze

HTL 38	2g
HTL 38	5g
HTL 38	25g

*M.P. *Gold Content*

Copper*

HTL 39	2g
HTL 39	5g
HTL 39	25g

Mother of Pearl Lustre

HTL 35	25g
HTL 35	100g

Yellow Lustre

HTL 136	25g
HTL 136	100g

Orange Lustre

HTL 36	25g
HTL 36	100g

Amber Lustre

HTL 34	25g
HTL 34	100g

*M.P. *Gold Content*

Red Lustre*

HTL 31	10g
HTL 31	25g

*M.P. *Gold Content*

Violet Lustre

HTL 139	10g
HTL 139	25g

*M.P. *Gold Content*

Green Lustre

HTL 33	10g
HTL 33	25g

*M.P. *Gold Content*

Blue Lustre

HTL 32	10g
HTL 32	25g

*M.P. *Gold Content*

Black Lustre

HTL 37	10g
HTL 37	25g

HTL

Gold & Precious Metals for Glass

10% Gold Content

Gold Glass Lustre

HTL 15	2 g
HTL 15	5 g
HTL 15	25 g

Platinum Glass Lustre

HTL 16	2 g
HTL 16	5 g
HTL 16	25 g

Mother of Pearl Lustre

HTL 35	25g
HTL 35	100g

Yellow Lustre

HTL 136	25g
HTL 136	100g

Orange Lustre

HTL 36	25g
HTL 36	100g

Amber Lustre

HTL 34	25g
HTL 34	100g

*M.P. *Gold Content*

Red Lustre*

HTL 31	10g
HTL 31	25g

*M.P. *Gold Content*

Violet Lustre

HTL 139	10g
HTL 139	25g

*M.P. *Gold Content*

Green Lustre

HTL 33	10g
HTL 33	25g

*M.P. *Gold Content*

Blue Lustre

HTL 32	10g
HTL 32	25g

*M.P. *Gold Content*

Black Lustre

HTL 37	10g
HTL 37	25g

*M.P. *Gold Content*

Bronze

HTL 38	2g
HTL 38	5g
HTL 38	25g

*M.P. *Gold Content*

Copper*

HTL 39	2g
HTL 39	5g
HTL 39	25g

Liquid gold and metallic lustres have a colloidal form and have a dark brown colour; they contain dissolved metals as the main component. If necessary, to ease the application of the product, the thinner HTL - 199 can be used up to a maximum of 3%. They are mainly applied by brush on earthenware and porcelain. Airbrush application is for professional use only. This application should always be on glazed objects, thoroughly clean and moisture free.

FIRING TEMPERATURE: EARTHENWARE

Orton Cone : 018 | *Celsius degrees C° :* 690°-700° | *Degrees Fahrenheit F° :* 1274 - 1292°

FIRING TEMPERATURE: STONEWARE/PORCELAIN

Orton Cone : 017-015 | *Celsius degrees C° :* 750°-815° | *Degrees Fahrenheit F° :* 1382 - 1499°

FIRING TEMPERATURE: GLASS

Celsius degrees C° : 500°- 550° | *Degrees Fahrenheit F° :* 932° - 1022°

	Gold			*Gold-based lusters*		*Lustres*		*Thinner*
SIZE	2 g.	5 g.	25 g.	10 g.	25 g.	25 g.	100 g.	100 g.
PACKAGING	1	1	1	1	1	1	1	1