

HAC

Academy

CONE 06 | 998 °C | 1828 °F



FOOD SAFE



NON TOXIC



LEAD FREE



READY TO USE



Pure white

HAC 5-501 200 ml
HAC 3-501 800 ml



Ocher dust

HAC 5-503 200 ml
HAC 3-503 800 ml



Daisy

HAC 5-502 200 ml
HAC 3-502 800 ml



Clementine

HAC 5-504 200 ml
HAC 3-504 800 ml



Scarlet velvet

HAC 5-505 200 ml
HAC 3-505 800 ml



Milk chocolate

HAC 5-513 200 ml
HAC 3-513 800 ml



Powdery rose

HAC 5-506 200 ml
HAC 3-506 800 ml



Dusty blue

HAC 5-507 200 ml
HAC 3-507 800 ml



Deep blue

HAC 5-509 200 ml
HAC 3-509 800 ml



Twilight

HAC 5-508 200 ml
HAC 3-508 800 ml



Turquoise

HAC 5-510 200 ml
HAC 3-510 800 ml



Spring grass

HAC 5-511 200 ml
HAC 3-511 3,78 L



Mountain fir

HAC 5-512 200 ml
HAC 3-512 800 ml



Oak

HAC 5-514 200 ml
HAC 3-514 800 ml



Sage

HAC 5-515 200 ml
HAC 3-515 800 ml



Panther

HAC 5-516 200 ml
HAC 3-516 800 ml

Engobes are finely ground clay based pigments. They are formulated to match the firing shrinkage and thermal expansion of the clay. Apply to wet or leather hard clay. The result of the raw firing is a matte, slightly rough surface. The piece can be fired again with our transparent clear glaze to get a brilliant sheen and intensify the color of the engobes.

C

Engobes can be applied on bisqueware using 2-3 layers for solid/opaque finish or use as a one stroke watercolor painting technique. Most of colorobbia art engobe colors can be fired up to cones 7/8 stoneware firing temperature. Some colors might fade. Please test first. You may apply engobes on the bottom of wares and fire without stiling. Always test first.

FIRING TEMPERATURE

Orton Cone : 06 | Celsius degrees C° : 998 °C | Degrees Fahrenheit F° : 1828 °F

SIZE	6,7 oz. / 200 ml.	27 oz. / 800 ml.
PACKAGING	6	6